

3-27-2021

RESEARCH OF THE PROCESS OF CONTINUOUS HYDROGENATION OF BENZENE IN THE PRESENCE OF MODIFIED CATALYSTS

B Kedelbaev Dr. Professor

South Kazakhstan State University named after M.Auezov, Kazakhstan, kedelbaev@yandex.kz

K Lakhanova PhD

International Kazakh-Turkish University named after. H.A. Yasawi, gani5@mail.ru

G Iztleuov

South Kazakhstan State University named after M. Auezov, Kazakhstan

Sadritdin Turabdzhanov Dr., Professor

Tashkent state technical university named after Islam Karimov, Tashkent, Uzbekistan

Follow this and additional works at: <https://uzjournals.edu.uz/btstu>

 Part of the [Mechanical Engineering Commons](#)

Recommended Citation

Kedelbaev, B Dr. Professor; Lakhanova, K PhD; Iztleuov, G; and Turabdzhanov, Sadritdin Dr., Professor (2021) "RESEARCH OF THE PROCESS OF CONTINUOUS HYDROGENATION OF BENZENE IN THE PRESENCE OF MODIFIED CATALYSTS," *Technical science and innovation*: Vol. 2021 : Iss. 1 , Article 1. DOI: <https://doi.org/10.51346/tstu-01.21.1-77-0099>
Available at: <https://uzjournals.edu.uz/btstu/vol2021/iss1/1>

This Article is brought to you for free and open access by 2030 Uzbekistan Research Online. It has been accepted for inclusion in Technical science and innovation by an authorized editor of 2030 Uzbekistan Research Online. For more information, please contact sh.erkinov@edu.uz.

- [12] K. Rakhmatullayev, A.S. Giyasov. Thallium Extraction (III) in the Presence of Chloride ions and Dimethylpharmamide and its Complexation in the Organic Phase. Bulletins of higher education institutions. Chemistry and Chemistry Technology 1984. T.27. Issue 9. Pages - 1028-1031 (in Russian).
- [13] E.I. Larinova, E.V. Zabolovskaya, K.A. Bulygina. Method of joint photometric determination of chromium (VI) and iron (III) using curve fitting method. Tomsk Polytechnic University. Siberia Science Bulletin 2015 (in Russian).
- [14] F. Espandi, R.A. Alieva, F.S. Alieva, F.L. Charagov. Spectrophotometric study of complexation of iron (III) with bioacetylacetaethylenediamine in the presence of trite x-114, antipyrine and cordiamine. Baku State University. Medical Sciences Series. №3, 2013(in Russian).
- [15] E.V. Makusheva, T.F. Dekhtyar. Methods for the determination of iron (III) ion. //Chemical Sciences//. //International Scientific Journal " Internauka// № 1 (23), 2017.
- [16] R.A. Aliyeva, A.V. Ayvazova, F.E. Espandi, F.M. Chiragov. Determination of iron (III) in various apple cultivars using the spectrophotometric method. Izvestiyavuzov. applied chemistry and biotechnology. Vol. 8 № 1 2018.
- [17] A.B. Shehata, G.G. Mohamed, M.A. Gab-Allah. A simple spectrophotometric method for determining iron in crude oil. Petrochemistry, 2017, Vol. 57, № 6, c. 630–634.
- [18] Zh.M. Arstamyanyan, G.T. Mushegyan, S.D. Yeghiazaryan. Extraction-photometric determination of iron by methyl green in natural and waste water. Journal of organic chemistry. Armenia №3, 2003.
- [19] K.A. Kuliyeu. Dimercaptophenols as analytical reagents for extraction-photometric iron (III). "Factory laboratory. Diagnostics of materials". 2017. Vol. 83. № 3.
- [20] B. Pahlavanpour, M. Thompson, L. Thome. Analyst. 1980, August. Vol. 105. Pp. 756–761.

UDC 541.128

RESEARCH FOR THE CONTINUOUS BENZENE HYDROGENATION PROCESS IN THE PRESENCE OF THE MODIFIED CATALYSTS

B.Sh. Kedelbaev^{1*}, K.M. Lakhanova², G.M. Iztleuov¹, S.M. Turabdzhonov³

¹M. Auezov South Kazakhstan State University, 5 Tauke-khan ave, 160012, Shymkent, Republic of Kazakhstan

²Yassawi International Kazakh-Turkish University, B. Sattarkhanov St. 29, Turkestan, SKO, Kazakhstan

³Tashkent State Technical University named after Islam Karimov, 100095, University St. 2, Tashkent, Uzbekistan

Abstract. *The technology has been developed for the production of unsaturated alloy nickel hydrogenation catalysts. The results of the study of the phase, chemical compositions and structure of nickel alloys and catalysts showed that the ferroalloy introduction as a modifying additive affects the NiAl₃ / Ni₂Al₃ ratio. The studied alloying metals are practically insoluble in*

alkali and exist in the catalyst in dissolved states. All these changes favorably affect the catalytic properties of modified nickel catalysts in the benzene hydrogenation reaction. A systematic study of the stationary catalyst activity with addition of ferroalloys in the continuous catalytic benzene hydrogenation was carried out with a wide variation of the process parameters. All catalysts are dominated by particles with $R = 0-2$ microns, the concentration of which reaches 75-89%. Table 1 shows that, with an increase in the amount of additives in alloys from 3 to 9% by weight, the concentration of particles with $R = 0-2 \mu\text{m}$ in catalysts decreases differently within 89-75%, depending on the nature of the alloying metals. In addition, modifying additives also increase the concentration of particles with $R = 2-4 \mu\text{m}$. The results of optical microscopy show that almost all studied skeletal nickel catalysts are enriched by 90-99% in particles with $R_{\text{max}} = 1-5 \mu\text{m}$. A systematic study of the stationary catalyst activity with addition of ferroalloys in the reaction of continuous catalytic benzene hydrogenation with a wide parameter variation of the technological process has been carried out. At the same time, it is highly active, stable and selective for cyclohexane new stationary catalysts for industrial purposes operating at temperatures up to 140°C and pressure up to 8 MPa.

Keywords: *catalyst, nickel, aluminum, benzene, cyclohexane, cadmium plating, promotion, ferroalloys*

INTRODUCTION. The petrochemical potential of industrialized countries is determined by the volume of production and processing of aromatic hydrocarbons. It is these products that form the raw material base of the organic synthesis industry [1]. At present, the general trend in the development of the oil industry in the world is the tightening of environmental legislation aimed at reducing harmful emissions when using fuels and oils, as well as a constant increase in requirements for the quality of petroleum products.

The tightening of requirements and standards for quality leads to the need for advanced development of technologies for their production. Research into the hydrogenation of aromatic hydrocarbons is one of the most important problems in petrochemistry due to the tightening of requirements for modern motor fuels, recently in accordance with the requirements of Euro-5 (2)

The problem of the aromatic hydrocarbon content reduction can be solved by many methods, including their extraction by adsorption or extraction, as well as conversion into other, less harmful compounds. One of the most effective methods for improving the operational properties of fuels, in particular gasoline, is their hydrodearomatization, which consists in the process of hydrogenation of aromatic hydrocarbons in the presence of catalysts.

From this point of view, the solution of the problems of dearomatization of such compounds is an urgent problem.

A review of the literature data on the hydrogenation of benzene [3-7] shows that in many cases the process is carried out in the vapor phase at temperatures of $250-325^\circ\text{C}$ and a hydrogen pressure of 10.0-27.0 MPa. Platinoids are also used as catalysts. Naturally, under these conditions, the products of isomerization and cleavage are observed in the catalyst, which reduces the quality of the target product, cyclohexane.

New methods have been discovered to increase the activity, stability and mechanical strength of nickel catalysts by introducing additives of other metals into the alloy at the time of

their preparation [8-10]. As a result, effective catalysts have been found that accelerate the benzene hydrogenation reaction. The hydrogenation of aromatic hydrocarbons was carried out on them in a reactor periodic action in the temperature range 20 - 200 ° C and hydrogen pressure 0.1-15.0 MPa.

On an industrial scale, in the production of cyclohexane, coprecipitated oxide copper-chromite catalysts are widely used [11-13], although they are not devoid of significant disadvantages in terms of catalytic and operational properties in hydrogenation processes. In connection with the above, researchers have proposed numerous modified Ni, Cu, Co -alloy catalysts [14-15], which have not yet acquired industrial application in these industries. Therefore, it is urgent to improve these catalysts by modifying them in order to further increase their selectivity, operational and catalytic properties in the processes of hydrogenation of aromatic hydrocarbons in the liquid phase.

In works (16-17) it is shown that alloyed nickel catalysts modified with ferroalloys are the cheapest and most accessible in hydrogenation processes.

This article presents the results of a study of the hydrogenation of benzene to cyclohexane on alloyed nickel catalysts modified with ferroalloys (FS) - ferromolybdenum (FMo), ferrosilicochromium (FSKh) and ferrosilicocalcium (FSK).

EXPERIMENTAL PART. The initial alloys were prepared in a high-frequency furnace, the content of the components in them varied (in wt%): nickel - 45-49, aluminum - 50, FS - 1.0-5.0. The original alloys were used in the form of various fractions, depending on the method of their study.. So, Alloys with different diameters were used for metallographic and local X-ray spectral analysis. So for continuous hydrogenation used alloys with a grain diameter and 3-5 mm. Physicochemical studies were carried out in the presence of powdered alloys and catalysts. For this, the starting alloys were crushed and sieved through a sieve 0.25 mm. The catalysts were prepared by leaching the alloys with a 20% aqueous solution NaOH in a boiling water bath for 1 hour, then washed with water from alkali to neutral reaction with phenolphthalein. The catalyst was activated directly in the reactor itself. In this case, a granular alloy with linear dimensions of 2-4 mm (100 g) was placed in a special glass attached to the bottom of the reactor and the leaching process was carried out with a 10% aqueous solution of sodium hydroxide.

In the course of leaching with the help of a metering pump, the reactor was first filled with distilled water, and then an alkali solution was fed from the "measuring tank". The degree of aluminum removal was monitored by the evolution of hydrogen, the amount of which was changed with a gas meter. After the release of the required amount of hydrogen to the leached catalyst, using the same pump, to stop the leaching process and wash the catalyst from alkali residues to pH-7, water was supplied from the "measuring tank". The amount of aluminum removed from the consistency was about 10-15%.

To identify the obtained alloys and catalysts, studies of their structure and adsorption properties were carried out. For this purpose, the catalysts were prepared by leaching the alloys with a 20% aqueous solution of sodium hydroxide in a boiling water bath for 1 hour. Samples taken during the hydrogenation studies were analyzed by chromatographic and partially refractometric methods with the construction of calibration curves relative to benzene, cyclohexane and

Chemistry and chemical technology

cyclohexene. The sensitivity of the detector of the chromatograph in a flow of helium to the assumed composition of the catalyzate, which is formed during the hydrogenation of benzene according to the Porter Formula $A = S \cdot V \cdot \ln \frac{1}{q} \cdot \frac{1}{v}$, where S is the peak area, cm^2 ; V -velocity of the gas-carrier $\text{ml} / \text{min.}$, V_1 -recorder sensitivity mv / s ; v - speed of the chart tape $\text{cm} / \text{min.}$, q - quantitative value of the sample, mg . The calibration coefficients were for cyclohexane $K_{c6n6} = 0.974$, $K_{c6n10} = 0.972$, for cyclohexane $K_{c6n12} = 1.057$. The detector sensitivity was $A_{c6n6} = 3.5 \cdot 10^{-2}\%$; by $A_{c6n10} = 4.6 \cdot 10^{-2}\%$; by $A_{c6n12} = 6.8 \cdot 10^{-2}\%$; and for propane = $2 \cdot 10^{-2}\%$. The found values of the detector sensitivity are, respectively, for benzene- $3.5 \cdot 10^{-2}\%$, for cyclohexane - $6.8 \cdot 10^{-2}\%$, based on cyclohexene- $4.6 \cdot 10^{-2}\%$. Technical characteristics of the sensitivity of the device relative to propane- $2 \cdot 10^{-2}\%$. The catalytic activity of the studied catalysts was compared mainly by chromatography data.

RESULTS AND DISCUSSION. Since nickel catalysts have been studied sufficiently[nine], we limited ourselves to presenting data on phase composition, structure; specific surface area of alloys and catalysts based on aluminum-nickel alloys modified with ferroalloys.

It should be noted that in the literature, the influence of ferroalloys on the physicochemical properties of alloyed aluminum-nickel catalysts is insufficiently illuminated. In this regard, we have investigated the effect of FSC, FMo, and FSH on the phase composition and structure of aluminum-nickel alloys and catalysts.

From table 1, it can be seen that modifying additives have a significant effect on the qualitative and quantitative composition and structure of the starting alloys and catalysts. The catalysts are composed of skeletal nickel- Al_2O_3 , Ni_2Al_3 and ferroalloy. Modifying additives do not affect the crystal lattice parameter of nickel, but they significantly grind its crystals, and also increase the specific surface area of the catalyst before $130.0 \text{ m}^2 / \text{g}$.

Table 1.

Characteristics of aluminum-nickel alloys and catalysts with addition of ferroalloys

Modifying additives	Alloys					Catalysts		
	phase area, %			Fx	NiAl ₃	Crystal lattice parameter (a), nm	Crystal size (L), nm	Specific surface area (S) m ² / g
	NiAl ₃	Ni ₂ Al ₃	Al + NiAl ₃ eutectic					
Ni - Al = 50 - 50								
-	50y	40	10	-	1.25	0.353	5.4	1.5
Ni - 50% Al - ΦCTO								
3-10.0	50	39	7	3	1.28	0.353	4.7	110
Ni - 50% Al - ΦMo								
3-10.0	48	44	12	6	1.33	0.353	4.6	130
Ni - 50% Al - FSH								
3-10.0	44	39	12	8	1.33	0.353	3.2	122.4

Thus, the introduction of ferroalloy additives into an aluminum-nickel alloy significantly affects the phase composition, structure, and specific surface area of skeletal nickel catalysts. The results of X-ray and X-ray spectral studies have shown that the modifying metals in the catalysts are not in a free, but in a dissolved state. The dispersion of catalysts affects the activity and selectivity of catalysts, and the main reason for the change in activity is the dispersion of catalyst grains and an increase in the efficiency factor, which simulates chemical promotion.

The particle size distribution of skeletal nickel catalysts with additions of FSKh, FSK and FMo ferroalloys has been investigated. The data of microscopic and electron microscopic studies of the particle size distribution of skeletal nickel catalysts are shown in Table 1.

All catalysts are dominated by particles with $R = 0-2$ microns, the concentration of which reaches 75-89%. Table 1 shows that, with an increase in the amount of additives in alloys from 3 to 9% by weight, the concentration of particles with $R = 0-2 \mu\text{m}$ in catalysts decreases differently within 89-75%, depending on the nature of the alloying metals. In addition, modifying additives also increase the concentration of particles with $R = 2-4 \mu\text{m}$. The results of optical microscopy show that almost all of the studied skeletal nickel catalysts are enriched by 90-99% in particles with $R_{\text{max}} = 1-5 \mu\text{m}$.

Table 2.

Results of microscopic and electron microscopic studies of skeletal nickel catalysts.

Catalyst	Particle size distribution% by size R, μm					
	0-2	2-4	4-6	6-8	> 8	T3
Ni (50% Al)	77	8	6	2	7	0.12
Ni-3-10% FSK	78	8	8	4	2	0.45
Ni-3-10% FMo	85	6	5	2	1	0.35
Ni-3-10% FSH	83	6	6	3	1	0.36

The results of studying the particle size distribution using optical microscopy and an electron microscope confirm the enrichment of skeletal nickel catalysts with particles with $R_{\text{max}} = 1 \mu\text{m}$. Modifying metals increase the proportion of particles with a size of 0-6 microns.

We have studied [2] the porous structure of skeletal nickel catalysts with addition of ferroalloys. Argon sorption isotherms show that the forms of hysteresis loops for most of the modified nickel catalysts are characterized by a parallel arrangement of adsorption and desorption branches in the middle range of relative pressures and, according to the de Boer classification, belong to type A, which indicates the prevalence of cylindrical pores [3].

Table 3. the parameters of the porous structure of skeletal nickel (50% Al) catalysts with addition of ferroalloys are given. It is seen that modifying ferroalloys mainly increase SBET, SKUM, respectively, to 110-130.5 and 85-98 m^2 / g ; pore volume - 1.1-1.4 times; effective pore radius REFF - 1.06-1.5 times. A simultaneous increase in the specific surface area and pore volume with relatively high effective radius apparently due to the dispersion of the nickel phase of the catalysts with modifying metals.

Table 3.

Parameters of the porous structure of skeletal aluminum-nickel catalysts with addition of ferroalloys.

Catalyst	SBET, m^2 / r	SCUM, m^2 / r	$\frac{S_{\text{БЭТ}} - S_{\text{КУМ}}}{S_{\text{БЭТ}}}$	Vthr, cm^3 / r	Reff, Å	Isother m type
----------	----------------------------------	----------------------------------	--	-----------------------------------	---------	-------------------

Chemistry and chemical technology

			100%			
Ni (50% Al)	105	75	28.5	0.105	30	A
Ni - 3-10% FSK	110	85	22.7	0.120	34	A
Ni - 3-10% ΦMo	130.5	98	24.9	0.138	36	A
Ni - 3-10% FCX	123.7	92	23.9	0.148	36	A

The results of studying the kinetics of desorption of H₂ from skeletal nickel catalysts with addition of ferroalloys are given in Table 3. It can be seen that the desorption of hydrogen starts from 0°C and occurs continuously up to 6000°C and above, but at an unequal rate; maximum in the areas 100-1400°C and 150-2000°C. Modifying metals have practically no effect on the nature of the thermal desorption curve for skeletal nickel (50% Al), but change the magnitude of the peaks in different ways, shifting their position mainly to the low-temperature region [4]. The thermal desorption curves clearly show two forms of hydrogen, the desorption of which is carried out in the range of 0-2100°C and 210-6000°C. The first form is desorbed according to the first order equation, and the second form is of the second order. Skeletal FSiCr catalysts exhibit the highest hydrogen capacity, the total volume of desorbed hydrogen up to 6000°C reaches 51.0-55.0 cm³ / g. The sorption capacity of the studied nickel-alumina catalysts occurs through maxima corresponding to 5, 0% content of modifying additives. It should be noted that alloying metals predominantly decrease the concentration of relatively strongly adsorbed forms of H₂, increasing the first weakly adsorbed one. The addition of metals 1.1-1.5 times increases the first form of adsorbed hydrogen.

Table 4.

Thermal desorption of H₂ from skeletal aluminum-nickel catalysts with addition of ferroalloys.

Catalyst	The volume of desorbed H ₂ from 1 g catalyst (up to 6000°C) cm ³ / g	Selection areas					
		I - (0-2100°C)			II - (210-6000°C)		
		Quantity H ₂ , cm ³ / g	T _{max} , °C	Peak edes, kJ / mol	Quantity H ₂ , cm ³ / g	T _{max} , °C	Peak edes, kJ / mol
		H ₂ Me			Me \\ H		
Ni (50% Al)	43.0	20.8	140	34.3	21.0	250	67.9
Ni-3% FSK	45.5	23,7	145	35.5	21.8	254	68.3
Ni-5% FSK	44.4	24.9	130	30.8	19.5	240	65.0
Ni-3% FSH	48.8	27.3	130	30.0	21.5	235	64.0
Ni-5% FSH	51.5	29.6	125	29.0	21.9	225	63.0
Ni-3% FMo	53.5	33,7	115	27.6	19.8	200	56.0

Ni-5% FMo	53.0	35.8	120	28.5	19.2	180	53.7
-----------	------	------	-----	------	------	-----	------

In addition, the first and second forms of adsorbed H₂ are desorbed at relatively low temperatures (I-form - 100-1400C, II-form - 150-2400C) and with a lower Edes value (I-form - 24-30 kJ / mol, II-form - 50.5-65.0 kJ / mol) the amount of weakly adsorbed forms of hydrogen in promoted catalysts reaches 50-60% of the total amount of desorbed H₂. Skeletal Ni-ΦSiCr catalysts exhibit the highest sorption capacity with respect to all forms of H₂. The rest of the catalysts for decreasing the sorption capacity for H₂ are arranged in a row: Ni-FMo > Ni-FSK > Ni-FSK > Ni (50% Al).

So the amount of form of desorbed hydrogen is bound. They are associated with a change in the surface structure of the contact: the ratio of intermetallic nickel (Ni₁₃ / Ni_{2A13}), the presence of surface oxides, which is reflected in the Me - H bond energy.

We have previously determined the structure and adsorption properties of the obtained alloys and catalysts. Subsequently, these catalysts were tested in the process of continuous hydrogenation of benzene in a flow-through column-type unit. During the experiments, the alloys were activated with 10% sodium hydroxide solution. During the first leaching, 30% of aluminum was removed, the catalyst was saturated in a stream of hydrogen for 18 hours at a process temperature of 1600C and a pressure of 0.5 MPa. The benzene feed rate varied from 60 to 120 ml / h. An increase in the hydrogen pressure from 5 to 8 MPa made it possible to reveal that, with an increase in the hydrogen pressure to 6 MPa, the degree of benzene conversion increases, and a further increase in pressure does not affect the catalyst activity.

Table 4 shows that stationary ferroalloy catalysts exhibit absolute activity with respect to cyclohexane and their activity is higher than that of a commercial nickel-titanium catalyst. The values of contact loads overcooked by 30% for aluminum Ni-FMo catalysts at 120°C and 10 MPa reach 0.70 h⁻¹, respectively, which is 2.3 times higher than that of industrial nickel-titanium contacts. The test results showed that the Cu-Al-FMo catalyst is 1.9 times more productive and 2.0 times more stable than the industrial nickel-titanium contact.

Table 5.

Results of continuous hydrogenation of benzene in a flow column unit.

Catalyst	T°FROM	Catalyst composition		W h-1	Relative continuation Process
		Cyclohexane	Benzene		
Ni -Al	90-100	78-85	15-22	0.12-0.21	210
	110-120	81-92	8-19	0.26-0.28	
	130-140	87-98	-13	0.31-0.35	
Ni-Al-FSK	110-120	94-98	2-6	0.50-0.64	254
	90-100	94-97	3-6	0.42-0.63	
	110-120	96-99.8	0-4	0.53-0.70	
Ni-Al-FSH	110-120	98-99.8	0-2	0.69-0.87	410
	90-100	96-99	1-4	0.47-0.72	
	130-140	99.5-99.8	0.5-0.1	0.94-1.2	
Ni-Al-FMo	90-100	96-98	4-2	0.48-0.7	420
	110-120	99-99.8	1-0.1	0.65-0.82	
	130-140	99.5-99.8	0.5-0.1	0.94-1.2	
Ni-Tiprom	90-100	84-96	10-16	0.40-0.44	

Chemistry and chemical technology

	40-120	84-95	5-16	0.47-0.50	202
	130-140	98-99.8	0-10	0.50-0.60	

CONCLUSION

Thus, we have synthesized for the first time a series of new samples of modified alloyed aluminum-nickel catalysts for the hydrogenation of aromatic hydrocarbons. Their chemical, phase and granulometric compositions, porous structure, adsorption, desorption capacities for hydrogen, as well as the processes of benzene and toluene hydrogenation in their presence have been studied. The promoting effect of ferroalloys (FMo, FSK, FSKh) on the physicochemical and adsorption properties of alloyed aluminum-nickel catalysts, as well as on their catalytic properties in the reaction of liquid-phase hydrogenation has been studied benzene, toluene... The principles of selection of catalysts and modifying additives are proposed. It was found that modifying additives disperse skeletal nickel crystals, increase the specific surface area, the proportion of micropores, the pore volume and their effective radius, as well as the sorption capacity of aluminum-nickel catalysts relatively weakly adsorbed on their surface forms of hydrogen, which contributes to an increase in the catalytic activity of the skeletal catalysts modified by the indicated ferroalloys. A systematic study of the activity of stationary catalysts with addition of ferroalloys in the reaction of continuous catalytic hydrogenation of benzene with a wide variation of the parameters of the technological process has been carried out. At the same time, highly active, stable and selective for cyclohexane new stationary catalysts for industrial purposes operating at temperatures up to 140°C and pressure up to 8 MPa. The Ni-Al-FMo catalyst is recommended for introduction into the production of cyclohexane from benzene [3].

References:

- [1] Molina R., Poncelet G. Hydrogenation of benzene over alumina-supported nickel catalysts prepared from Ni (II) acetylacetonate. // *J. Catal.* 2001. V. 199. No. [2] P. 162-170.
- [2] Viller et al. *World Fuel Charter // Oil refining and petrochemistry.* 1999. No. 6. S. 50-55.
- [3] Sheldon G. Shore, Errun Ding, Colin Park, Mark A. Keane. Vapor phase hydrogenation of phenol over silica supported Pd and Pd-Yb catalysts. // *Catalysis Communication* 3, 2002. P.77-84.
- [4] Armaroli T., Bevilacqua M., Trombetta M., Alejandre AG, Ramirez J., Busca G. An FT-IR study of the adsorption of aromatic hydrocarbons and of 2,6-lutidine on H-FER and H-ZSM-5 zeolites. // *Appl. Catal. A Gen.* 2001. V. 220. P. 181-190.
- [5] Zhu Y., Lee CN, Kemp RA, Hosmane NS, Maguire JA Latest developments in the catalytic application of nanoscaled neutral group 8-10 Metals. // *Chem. Asian J.* 2008. V. 3.No. 4. P. 650-662.
- [6] Turadzhyanov S., Kedelbaev B., Tashkaraev R. Hydrogenation of Benzene on Nickel Catalysts Promoted by Ferroalloys. *Theoretical Foundations of Chemical Engineering* ,, Yol. 47, No. 5, 633-634, 2013.

- [7] Konuspayev S.R., ShaimardanM., Nurbaeva D.R., Auezov A.B., Voronin I. Rhodium catalysts for hydrogenation of benzene and its homologues in various solvents, *Petrochemistry*, volume 50, No. 1, 2010, pp. 48-51.
- [8] Hou Y., Kondoh H, Ohta T., Gao S. Size-controlled synthesis of nickel nanoparticles. // *Appl. Surf. Sci.* 2005. V. 241. No. 1-2. P. 218-222.
- [9] Butov, GM, Hydrogenation of benzene on ruthenium catalysts supported on aluminum and rare earth oxides. *Refining and petrochemicals*, 2005, No. 11 .- S. 14-16.
- [10] Kameoka S., Kimura T., Tsai AP A Novel Process for Preparation of Unsupported Mesoporous Intermetallic Ni-Zn and Pd-Zn Catalysts. // *Catal. Lett.* 2009. V. 131. No. 1- P. 219224.
- [11] MarcinPisarek, MariuszLukaszewski, PiotrWiniarek, PiotrKedzierzawski, Maria Janik-Czachor. Influence of Cr addition to Raney Ni catalyst on hydrogénation of isophorone. // *Catalysis Communications* 10, 2008. P.213-216.
- [12] Mashkovsky IS, Baeva GN, Stakheev AY, Voskoboynikov TV, Barger PT Pd / Al₂O₃ catalyst for selective hydrogenation of benzene in benzene-toluene mixture. // *Mendelev Comm.* 2009. V. 19.No. 2. P. 108-109.
- [13] Navalikhina M.D., Krylov O.V. Development and industrial use of new hydrogenation catalysts. // *Kinetics and Catalysis.* 2001. T. 42. No. 1. S. 86-98.
- [14] Wang S., Lin W., Zhu Y., Xie Y., Chen J. Preparation and catalytic performance of monolayer-dispersed Pd / Ni bimetallic catalysts for hydrogenation. // *Front. Chem. China.* 2008. V. 3. No. 2. P. 161-165.
- [15] Loviat F., Czekaj I., Wambach J., Wokaun A. Nickel deposition on γ -Al₂O₃ model catalysts: An experimental and theoretical investigation. // *Surf. Sci.* 2009.V. 603. No.4 P. 2210-2217.
- [16] Kedelbaev B., Turtabayev S,Shalabaeva G., Sarbaeva K.Synthesis and Research of the Nickel Catalysts of Liquid-Phase Hydrogenation of Benzene, *Contemporary Engineering Sciences*, Vol. 8, 2015, no. 3, 127 – 135.
- [17] Turadzhanov S., Kedelbaev B., Tashkaraev R.Hydrogenation of Benzene on Nickel Catalysts Promoted by Ferroalloys. *Theoretical Foundations of Chemical Engineering* ,, Yol. 47, No. 5, 633-634, 2013.

UDC 664.047:665.3

SIMULATION OF A THREE-QUASI-HARDWARE UNIT FOR OIL-CONTAINING MATERIAL PRESS

A.A. Artikov¹, A.A. Akbarokhodaev^{1*}, M.S. Narziev², Y. Savriev²

¹*Tashkent Institute of Chemical Technology 32 Navoi st, 100011, Tashkent city, Republic of Uzbekistan* ²*Bukhara Engineering and Technology Institute, Navoi ave., Bukhara*

Abstract. *This article analyzes an oil press apparatus, which has found wide application in the production of vegetable oil. Previously, a computer model of the oil extraction process with concentrated parameters was compiled and investigated. Continuing the research, the*